

Table 1. Complete List of Significant Drill Intersections

Hole	From (feet)	To (feet)	Width (feet)	Width (meters)*	Cu %	Zn %	Pb %	Ag (g/t)	Au (g/t)	Zone
CMR06-01	338.2	355	16.8	5.12	0.25	11.18	0.14	47.6	0.14	RW Zone
CMR06-02	338.4	341	2.6	0.79	0.04	19.50	0.01	4.7	0.02	RW Zone
CMR06-02	528.5	583	54.5	16.61	0.03	1.20	0.01	0.5	0.01	stringers
CMR07-07	497.2	543.1	45.9	13.99	4.09	7.35	0.22	50.9	0.40	RW Zone
Includes	519	541.8	22.8	6.95	6.83	5.41	0.21	81.3	0.62	RW Zone
CMR07-09	502.1	581.6	79.5	22.56*	1.21	7.15	0.45	55.4	0.78	SW Zone I
Includes	502.1	561	58.9	17.95	1.12	8.04	0.56	66.7	0.95	SW Zone I
CMR08-09	787	798.2	11.2	3.41*	0.16	10.98	0.03	18.2	0.08	SW Zone II
CMR08-10										NSV
CMR08-11	514.7	668.4	153.7	46.85*	1.47	5.50	0.39	25.5	0.44	SW Zone I
Includes	516	635	119	36.27	1.70	5.74	0.47	30.4	0.53	SW Zone I
Includes	529	615.9	86.9	26.5	1.94	6.75	0.59	37.2	0.66	SW Zone I
includes	573.8	603.1	29.3	8.9	4.32	5.21	0.04	36.9	0.85	SW Zone I
CMR08-11	915	991.1	76.1	23.2	1.34	7.43	0.35	91.3	0.70	SW Zone II
Includes	915	974.4	59.4	18.11*	1.61	8.55	0.39	106.3	0.84	SW Zone II
Includes	946	972.6	26.6	8.11	1.63	7.38	0.56	163.0	1.37	SW Zone II
Includes	964.4	972.6	8.2	2.5	2.03	7.27	0.41	369.3	3.52	SW Zone II
CMR08-11	1153.3	1194.6	41.3	12.59*	0.49	6.77	0.15	25.8	0.30	SW Zone III
Includes	1153.3	1177.9	24.6	7.5	0.46	8.19	0.30	30.6	0.24	SW Zone III
CMR08-12										Abandoned
CMR08-13	569	606	37	11.28*	3.14	0.58	0.01	24.7	0.15	SW Zone Ia
Includes	581.2	603	21.8	6.64	4.12	0.69	0.01	34.1	0.20	SW Zone Ia
CMR08-13	685.4	784.9	99.5	30.33*	0.98	1.00	0.02	6.1	0.16	SW Zone Ib
Includes	685.4	724.2	38.8	11.83	1.42	0.74	0.01	7.1	0.23	SW Zone Ib
CMR08-14	580	732.2	152.2	46.39*	2.92	2.98	0.01	17.5	0.20	SW Zone I
Includes	605.4	732.2	126.8	38.65	3.25	3.22	0.01	19.6	0.23	SW Zone I
Includes	612.4	662.3	49.9	15.21	5.22	1.75	0.01	21.1	0.30	SW Zone I
Includes	634.3	662.3	28	8.53	6.52	0.61	0.01	26.4	0.37	SW Zone I
Includes	713.9	732.2	18.3	5.58	1.76	14.36	0.01	40.2	0.21	SW Zone I
CMR08-14	1372	1453	81	24.69*	0.28	1.91	0.31	31.5	0.20	SW Zone II
CMR08-15										NSV
CMR08-16	427	447	20	6.1	1.10	0.05	0.01	0.3	0.03	stringers
CMR08-16	699	714	15	4.57	0.37	0.33	0.01	1.2	0.03	SW Zone I
CMR08-17	474	480	6	1.83	0.30	10.13	1.39	45.5	0.19	RW Oxide
CMR08-17	1059	1149.3	90.3	27.52*	2.60	3.57	0.17	28.2	0.35	SW Zone I
Includes	1066.7	1132	65.3	19.9	3.24	0.76	0.01	20.1	0.33	SW Zone I
Includes	1066.7	1081.5	14.8	4.51	4.62	0.76	0.01	14.7	0.27	SW Zone I
Includes	1132	1149.3	17.3	5.27	0.84	13.64	0.75	63.8	0.51	SW Zone I
CMR08-17	1633.1	1648.9	15.8	4.82*	0.85	21.62	0.39	19.3	0.04	SW Zone II
CMR08-17	1752.8	1765	12.2	3.72*	0.20	3.85	0.14	21.9	0.22	SW Zone III
CMR08-18	723	728	5	1.52*	1.73	2.60	0.13	40.2	0.32	SW Zone III
CMR08-18	840.4	851.3	10.9	3.32*	2.83	4.66	0.03	23.6	0.43	SW Zone IIa
CMR08-18	915.4	929	13.6	4.15*	0.97	3.87	0.15	10.3	0.10	SW Zone IIb

Hole	From (feet)	To (feet)	Width (feet)	Width (meters)*	Cu %	Zn %	Pb %	Ag (g/t)	Au (g/t)	Zone
Includes	915.4	923.3	7.9	2.41	0.74	6.61	0.26	9.7	0.11	SW Zone II
CMR08-19	656.6	783	126.4	38.53*	0.69	7.25	0.18	25.6	0.22	SW Zone II
Includes	656.6	706.7	50.1	15.27	1.13	8.66	0.08	32.4	0.26	SW Zone II
CMR08-20										Abandoned
CMR08-21	578.5	609.6	31.1	9.48*	0.34	2.68	0.16	38.9	0.10	SW Zone III
Includes	604.7	609.6	4.9	1.49	0.83	4.69	0.24	131.6	0.36	SW Zone III
CMR08-21	714.7	735.3	20.6	6.28	0.30	2.85	0.01	3.6	0.04	SW Zone II
Includes	723	735.3	12.3	3.75	0.45	3.89	0.01	4.0	0.04	SW Zone II
CMR08-22	770	868.5	98.5	30.02*	1.97	5.83	0.2	37.8	0.25	SW Zone II
Includes	770	782	12	3.66	1.82	9.81	0.92	81.5	0.32	SW Zone II
Includes	807	831	24	7.32	2.94	6.96	0.21	62.8	0.38	SW Zone II
Includes	846.6	868.5	21.9	6.68	3.43	8.92	0.03	33.9	0.34	SW Zone II
CMR09-23	1157	1227	70	21.34*	2.76	0.50	0.01	9.7	0.10	SW Zone I
Includes	1163.5	1200	36.5	11.13	3.86	0.50	0.01	10.8	0.12	SW Zone I
CMR09-24	467	497	35	9.14	0.23	2.83	0.59	52.5	0.57	RW Oxide
Includes	470.5	487	16.5	5.03	0.22	1.53	0.95	84.9	0.92	RW Oxide
CMR09-24	1043.7	1105	61.3	18.68	1.16	4.15	0.10	30.7	0.30	SW Zone I
Includes	1043.7	1073.4	29.7	9.05*	1.89	5.16	0.02	27.4	0.30	SW Zone I
CMR09-25	488.9	508.5	19.6	5.97	0.10	1.47	0.01	0.5	0.01	Oxide Cu-Zn
CMR09-25	1104	1159.2	55.2	16.82*	0.11	1.41	0.03	13.3	0.16	SW Zone I
Includes	1142	1159.2	17.2	5.24	0.06	0.78	0.04	25.5	0.31	SW Zone I
CMR09-26	909.1	911.5	2.4	0.73	0.05	1.19	0.46	40.3	0.08	SW Zone III
CMR09-26	1052	1072	20	6.1*	1.52	9.17	0.02	18.0	0.18	SW Zone II
Includes	1055.1	1068.2	13.1	3.99	2.09	9.19	0.02	22.0	0.22	SW Zone II
Includes	1059.4	1068.2	8.8	2.68	3.17	8.06	0.02	29.4	0.30	SW Zone II
CMR09-27										NSV
CMR09-28	1148.8	1156.3	7.5	2.29*	3.55	4.69	0.05	80.1	0.28	SW Zone III
Includes	1151.5	1155	3.5	1.07	6.12	5.81	0.03	123.9	0.48	SW Zone III
CMR09-29	65	81.5	16.5	5.03	0.22	1.82	0.01	0.5	0.01	Oxide Cu-Zn
CMR09-29	629	686.8	57.8	17.62	0.02	0.55	0.04	1.7	0.02	stringers
CMR09-30	294	335	41	12.5*	0.13	0.52	0.94	74.5	0.39	RW Oxide
Includes	297	320	23	7.01	0.20	0.42	1.23	104.1	0.57	RW Oxide
Includes	302	310	8	2.44	0.35	0.64	2.45	178.1	1.03	RW Oxide
CMR09-30	495	520.7	25.7	7.83	0.13	2.65	0.01	0.6	0.01	Oxide Cu-Zn
CMR09-30	564.3	597	32.7	9.97	0.29	0.34	0.01	2.4	0.04	stringers
CMR09-30	1635	1750	115	35.05	0.02	0.70	0.01	0.5	0.01	stringers
Includes	1635	1650	15	4.57	0.02	2.61	0.01	0.8	0.01	stringers
CMR09-31	1180.5	1191.7	11.2	3.41*	0.18	1.98	0.07	8.7	0.01	SW Zone III
CMR09-32	800.2	804.5	4.3	1.31*	0.06	3.13	0.13	3.2	0.07	SW Zone III

* Denotes intersections used on accompanying long section.

Drill intercepts reported as core lengths are estimated to be 60-95% true width. Bold text denotes intervals at >2% copper or >20 meters at >1% copper. Averages are length x density weighted using density data obtained for each sample within a given interval. Historically the Company reported length weighted averages. Length x density averages more accurately represent the metal content of a given interval, and is common practice in reporting on massive sulphide deposits because of the wide range of densities they exhibit. The Company has adopted length x density weighting as standard procedure for this project.